## **1–7** Toward the Recovery of Uranium from Fuel Debris

Development of a Chlorination Method for Slightly Soluble Components



## Fig.1-18 Outline of a chlorination experiment with fuel debris from $MoCl_{\text{5}}$

A mixture of  $(U_{0.5}Zr_{0.5})O_2$  and MoCl<sub>5</sub> is sealed in a glass tube in vacuum. It is converted to chloride by homogeneous heating at 573–773 K and by-products are separated by distillation at 573 K under a temperature-gradient condition.

As a result of the accident at the TEPCO's Fukushima Daiichi NPS, the treatment of fuel debris generated by solidification of melted fuels has been studied. One possible treatment option that has been proposed is the application of pyrochemical reprocessing technologies of spent nuclear fuels to treat fuel debris. According to the pyrochemical method, uranium and plutonium in spent fuels are separated from fission products and recovered to a cathode by electrolysis in a molten salt. A large issue with this method is the development of a pretreatment technique for converting fuel debris into chlorides.

Conventional chlorination techniques using chlorine gas over 873 K require the use of corrosion-resistant structural materials. In contrast, the chlorination technique using molybdenum pentachloride (MoCl<sub>5</sub>) is expected to have advantages such as a lower reaction temperature, ease of handling the solid MoCl<sub>5</sub>. By-products of this method can also be efficiently separated from chloride products by distillation.

In this study, we propose a new chlorination method of fuel debris using MoCl<sub>5</sub> and study the applicability of this method through basic experiments.

Using uranium-zirconium oxide solid solution ((U<sub>0.5</sub>Zr<sub>0.5</sub>)O<sub>2</sub>)



Fig.1-19 XRD profiles of the product obtained from a reaction between  $(U_{0.5}Zr_{0.5})O_2$  and  $MoCl_5$ Observed peaks were identified as tetragonal UCl<sub>4</sub> obtained by

a chlorination reaction.



Fig.1-20 Appearance of the product after separation of byproducts

By chlorination of  $(U_{0.5}Zr_{0.5})O_2$ , green UCl<sub>4</sub> was obtained as a product (left side in the figure), and MoOCl<sub>3</sub> and ZrCl<sub>4</sub> by-products were separated by distillation (right side in the figure).

powder and sintered pellets as simulated fuel debris, chlorination experiments with MoCl<sub>5</sub> were conducted and the reaction principle of uranium chlorination and separation of by-products by distillation (Fig.1-18) were confirmed.

Regarding the chlorination reaction, most uranium in the sample was successfully converted to uranium tetrachloride (UCl<sub>4</sub>) at 573 K (for the powder) or 773 K (for the sintered particles) based on the following equation (Fig.1-19):

 $2(U_{0.5}Zr_{0.5})O_2 + 4MoCl_5 \rightarrow UCl_4 + ZrCl_4 + 4MoOCl_3$ 

By-products of this reaction include MoOCl<sub>3</sub> and zirconium tetrachloride (ZrCl<sub>4</sub>). These were successfully separated from UCl<sub>4</sub> by distillation at 573 K (Fig.1-20).

On the basis of these results, we proposed a new chlorination method for fuel debris using MoCl<sub>5</sub> and confirmed its applicability in principle.

These results were obtained in accordance with the project for development of the fuel debris characterization and treatment technologies as funded by the Agency for Natural Resources and Energy, Ministry of Economy, Trade and Industry of Japan (METI).

## Reference

Sato, T. et al., Chlorination of UO<sub>2</sub> and (U, Zr)O<sub>2</sub> Solid Solution using MoCl<sub>5</sub>, Journal of Nuclear Science and Technology, vol.52, issue 10, 2015, p.1253-1258.